

SAYERLACK BLANDESKEMA



	Hærder Normal	Blandingsforhold	Hærder Hurtig	Blandingsforhold	Fortynder	Blandingsforhold
Primer						
MU7001/00	MH2500	15% vol.	MH2501	15% vol.	MD0200	0 til 10 %
MU7001/13	MH2500	25% vol.	MH2501	25% vol.	MD0200	0 til 10 %
Topmaling						
MZ6010	MH2500	20% vol.	MH2501	20% vol.	MD0200	0 til 10 %
MZ6050	MH2500	20% vol.	MH2501	20% vol.	MD0200	0 til 10 %
MZ6080	MH2500	25% vol.	MH2501	25% vol.	MD0200	0 til 10 %

We cover your Business

LAKGRUPPEN